

SiSiB[®] STP31351

Silane Terminated Polyether Polymer

INTRODUCTION

SiSiB[®] STP31351 is an alkoxy silane terminated polyether polymer. It could be applied in moisture curing elastic sealant, elastic structure sealant and sealing coatings. Sealants based on SiSiB[®] STP31351 not only have excellent adhesion properties, but also have adhesion to broad range of substrates. Different from polyurethane and silicone system, this formulation have no solvent and isocyanate, as well as no bubbles and odor generated from curing. It is especially suitable for construction industry, transportation industry and general industry application.

PHYSICAL PROPERTIES

Component:	Silane Terminated Polyether
Appearance:	Pale yellow transparent liquid
Reactive Terminal Groups:	Trimethoxysilyl
CAS No.:	216597-12-5
Boiling point:	>250°C
Density 25°C:	1.0 g/cm ³
Viscosity 25°C:	35000-55000 cSt
Flash Point:	>237°C
Water-Soluble:	Virtually Insoluble

FEATURES

- ☐ High Activity , Medium-High Modulus
- ☐ High transparence
- ☐ Good adhesion strength and tensile elasticity
- ☐ Fast curing , non-tin catalysts used if needed, more eco-friendly
- ☐ Excellent aging and yellowing resistance
- ☐ Excellent water resistance , resistance to chemical corrosion
- ☐ Excellent storage stability
- ☐ Solvent free , odorless , eco-friendly

APPLICATION

SiSiB[®] STP31351 polymer is used as base polymer in elastic sealants, elastic structure sealants, encapsulate adhesives and coatings. The curing mode of the polymer is

SiSiB[®] STP31351

Silane Terminated Polyether Polymer

moisture curing. It can be made into a single component or two-components system.

- ☐ High Modulus sealant
- ☐ Transportation industry elastic sealant
- ☐ Industrial sealant
- ☐ Personal DIY sealant
- ☐ Eco-friendly decoration sealant

PROCESSING

SiSiB[®] STP31351 polymer dissolves readily in standard organic solvents. It is virtually insoluble in aqueous media, and react slowly releasing methanol and ethanol forming inert material. Despite its highly reactive terminal groups, uncatalyzed STP31020 is stable in air for several days. However, its reactivity with water or atmospheric humidity must be taken into account during storage and processing, since the material will slowly starts to condensate.

SiSiB[®] STP31351 polymer can be formulated by conventional methods and mixing processes. Water scavengers should be added to stabilize the formulations against premature curing during compounding or as a result of exposure to moisture during storage, particularly for vinyltrimethoxysilane.

PACKING AND STORAGE

SiSiB[®] STP31351 is supplied in 200Kg steel drum or 1000Kg IBC tote.

In the unopened original container SiSiB[®] STP31351 has a shelf life of one year in a dry and cool place.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

SiSiB[®] STP31351

Silane Terminated Polyether Polymer

Please send all technical questions concerning quality and product safety to:
support@SiSiB.com.

SINOPCC GROUP

AddSil, CoatSil, Kolark, PowSil, SinoSil, SiSiB, WinSil:
Trademark of SINOPCC Group Limited or its affiliated.
© 2018 SINOPCC Group Limited. All rights reserved.
For further information, please see www.SiSiB.com.