

ADDSiL™ 3278 Trisiloxane-Based Silicone Additive

INTRODUCTION

ADDSiL™ 3278 is a nonionic, organomodified trisiloxane surfactant designed to enhance wetting, flow, leveling, and air release in various coating systems. Its unique structure allows it to significantly reduce surface tension, promoting uniform application and improved surface appearance, even on challenging substrates.

KEY FEATURES & BENEFITS

- Low surface tension
- Excellent wetting properties for difficult-to-wet substrates
- Enhances flow and leveling characteristics
- Improves gloss and surface smoothness
- Reduces surface defects in cured coatings
- Effective at low usage levels
- Compatible with a variety of coating systems

PHYSICAL PROPERTIES

CAS No.	27306-78-1
EINECS No.	608-078-3
Boiling Point (760mmHg)	>150°C
Flash Point	116°C
Color and Appearance	Colorless to light amber liquid
Surface Tension (0.1%, mN/m)	< 21.5
Density (25°C)	1.03
Viscosity (25°C, cSt)	10-30

Note: These values are typical and are not intended for use as specifications.

APPLICATIONS

ADDSiL™ 3278 is a versatile silicone additive designed to enhance wetting, flow, and leveling properties in various coating systems. It is particularly effective in waterborne, solventborne, and radiation-curable (UV/EB) coatings and inks, promoting uniform finishes and reducing surface defects. Its ability to lower surface tension makes it suitable for high-gloss finishes and applications on challenging substrates in industrial and architectural coatings.

RECOMMENDED DOSAGE

The recommended dosage is 0.1% - 1.0% of the total formulations.

The above recommended levels can be used for orientation. Optimal levels

ADDSiL™ 3278 Trisiloxane-Based Silicone Additive

are determined through a series of laboratory tests.

PACKING

ADDSiL™ 3278 is supplied in 25Kg/Pail or 200Kg steel drum or according to customer's request.

HANDLING

This document does not contain the product safety information required for safe use. Before handling, please refer to the product and safety data sheets, as well as container labels, for information on safe usage, physical hazards, and health risks. Safety Data Sheet is available on the website, from the distributor, or by contacting SiSiB customer service.

STORAGE

When stored at temperatures between 10°C and 35°C in the original unopened containers, ADDSiL™ 3278 has a shelf life of 24 months from the date of production.

NOTE

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability.

We disclaim liability for any incidental or consequential damages.