

SINOSIL™ 9121 Addition-Cure RTV-2 Silicone Encapsulant

INTRODUCTION

SINOSIL™-9121 is a two-part, platinum-cured, thermally conductive liquid silicone rubber that cures at room or elevated temperature. With a thermal conductivity of up to 4.0 W/m·K and a low-viscosity, pourable consistency, it is ideal for potting and encapsulation of heat-generating electronic components. The cured elastomer offers excellent dielectric performance, elasticity, and strong thermal dissipation.

BENEFITS

- 1:1 mix ratio by weight
- High thermal conductivity: up to 4.0 W/m·K
- Excellent dielectric strength and volume resistivity
- Fast curing at elevated temperature
- Room temperature curable option
- Pink color for visual quality control
- RoHS and halogen-free compliant

PHYSICAL PROPERTIES

Color and Appearance	White/Pink liquid
Mixing Ratio (A/B)	1:1
Pot life (25°C, min)	45
Curing time (165°C, min)	20
Curing time (hrs)	24
Viscosity (A/B, mPa·s)	14,000/11,000

Properties Cured	
Appearance	Pink
Hardness (Shore A)	60
Dielectric Constant	10.0
Dielectric Strength	10-12 kV/mm
Volume Resistivity	$1 \times 10^{15} \Omega \cdot \text{cm}$
Thermal Conductivity	4.0 W/m·K

These values are typical and are not intended for use as specifications.

APPLICATIONS

- High-power electronics potting and thermal insulation
- EV battery modules and control units
-

SINOSIL™ 9121 Addition-Cure RTV-2 Silicone Encapsulant

- LED drivers, inverters, power supplies
- Heat-generating components requiring both insulation and thermal interface

PROCESSING GUIDE

Only components A and B with the same lot number should be used together. Prior to processing, both components must be stirred thoroughly in their original containers to ensure uniform dispersion of any settled fillers.

Surface Preparation

Ensure all substrates are clean and free from contaminants that may inhibit curing. Substances such as sulfur compounds, plasticizers, amines, urethanes, and organotin compounds can interfere with the platinum-catalyzed reaction. If substrate compatibility is uncertain, a small-scale test is recommended.

Mixing

To avoid premature gelling, tools used for handling Component A or the mixed compound must not contact Component B directly. Thoroughly mix both components at a 1:1 ratio by weight or volume. Degassing under vacuum is recommended to eliminate air entrapped during mixing or dispensing.

Curing

Cure time depends on temperature, part geometry, and the thermal mass of the substrate. Preliminary trials are recommended to optimize the curing cycle for specific applications.

PACKING

SINOSIL™ 9121 is supplied in 1kg kits, 20kg pails, or 200kg drums.

STORAGE

In the unopened original container, it has a shelf life of one year in a dry and cool place.

HANDLING

This document does not contain the product safety information required for safe use. Before handling, please refer to the product and safety data sheets, as well as container labels, for information on safe usage, physical hazards, and health risks. Safety Data Sheet is available on the website,

SINOSIL™ 9121 Addition-Cure RTV-2 Silicone Encapsulant

from the distributor, or by contacting SiSiB customer service.

NOTE

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability.

We disclaim liability for any incidental or consequential damages.