

SiSiB® STP92030 Silane Terminated Polyether Polymer

BACKGROUND

Polyurethane sealants offer good mechanical strength and are paintable but often contain solvents and have limited weather resistance. Silicone sealants provide excellent aging resistance, flexibility, and thermal stability but cannot be painted and may cause staining on absorbent surfaces.

Silane terminated polyether polymers (STP), also known as silane-modified polymers or MS polymers, combine the advantages of polyurethane and silicone without their weakness.

STP-based formulations are solvent-free and isocyanate-free, curing without bubble formation or odor release, and exhibit low VOC emissions with excellent paintability.

INTRODUCTION

SiSiB® STP92030 is a silyl-terminated polyether (STP) polymer designed as a base polymer in moisture-curing, low modulus adhesives, sealants, and coatings. When exposed to atmospheric moisture, it reacts through hydrolysis and crosslinking to create highly durable elastomeric materials.

SiSiB® STP92030 offers a balanced combination of durability, reactivity, and storage stability. Adhesives and sealants formulated with this polymer exhibit broad adhesion, good mechanical strength, and deliver excellent flexibility, weather resistance, and environmentally friendly curing performance.

FEATURES & BENEFITS

- Low viscosity, easy to process
- Low modulus with high elongation at break
- Excellent adhesion to various substrates without primer
- Superior durability, UV resistance, and weatherability
- Outstanding water and chemical resistance
- No solvent, no isocyanates, very low VOC
- Surface paintable after curing
- Excellent storage stability

PHYSICAL PROPERTIES

Appearance	Light yellow clear liquid
Boiling point	>250°C
Density 25°C	1.00
Viscosity (25°C, mPa·s)	6,000-10,000

SiSiB® STP92030 Silane Terminated Polyether Polymer

Flash point	>237°C
pH value	5.5-7.5
Water solubility/miscibility	Virtually insoluble

Note: These values are typical and not intended for specification purposes.

APPLICATIONS

- Construction sealants for joints and facades
- Industrial elastic adhesives
- Automotive bonding and sealing
- Renewable energy equipment bonding
- Flexible and durable protective coatings
- DIY/consumer sealants

PROCESSING

SiSiB® STP92030 silyl terminated polyether readily dissolves in standard organic solvents but is virtually insoluble in water. Despite its highly reactive terminal groups, uncatalyzed SiSiB® STP92030 remains stable in air for several days. However, its reactivity with water or atmospheric humidity must be considered during storage and processing, as exposure may lead to slow condensation.

SiSiB® STP92030 silyl terminated polyether can be processed using both hot and cold methods, and are suitable for both one component and two-component formulations. To prevent premature curing during formulation or exposure to moisture during storage, the addition of a water scavenger is recommended, SiSiB® PC6110 (vinyltrimethoxysilane) is commonly used.

PACKING

SiSiB® STP92030 is available in 200Kg steel drum and 1000Kg IBC tote.

STORAGE

SiSiB® STP92030 has a shelf life of 12 months from the date of manufacture when stored in its original, unopened containers below 30°C. After opening, containers should be tightly sealed to prevent contamination and moisture from entering the product.

HANDLING

This document does not contain the product safety information required for safe use. Before handling, please refer to the product and safety data sheets, as well as container labels, for information on safe usage, physical

SiSiB® STP92030 Silane Terminated Polyether Polymer

hazards, and health risks. Safety Data Sheet is available on the website, from the distributor, or by contacting SiSiB customer service.

NOTE

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability.

We disclaim liability for any incidental or consequential damages.

APPENDIX: UNDERSTANDING SEALANT MODULUS

Modulus	Key Characteristics	Typical Applications
Low	<ul style="list-style-type: none"> High flexibility Accommodates significant joint movement Exerts low stress on substrates 	<ul style="list-style-type: none"> Facade joints Curtain walls Glazing applications Expansion joints in concrete structures Areas with significant thermal or structural movement
Medium	<ul style="list-style-type: none"> Balanced flexibility and strength Suitable for general-purpose sealing Moderate stress on substrates 	<ul style="list-style-type: none"> Perimeter sealing of windows and doors Control joints in masonry Precast concrete panel joints General construction applications
High	<ul style="list-style-type: none"> High strength and rigidity Limited flexibility Exerts higher stress on substrates 	<ul style="list-style-type: none"> Structural glazing Non-moving joints Industrial applications requiring high strength Areas where joint movement is minimal