

## SiSiB® VF6965 Vinyl Fluoro Silicone Fluid

### CHEMICAL NAME

Vinyl-terminated (50% trifluoropropylmethylsiloxane) -dimethylsiloxane copolymer


### INTRODUCTION

SiSiB® VF6965 is a vinyl-terminated (50% trifluoropropylmethylsiloxane) - dimethylsiloxane copolymer designed for use in high-performance elastomers, sealants, coatings, and dielectric fluids. The presence of trifluoropropyl groups imparts excellent solvent resistance, chemical stability, and compatibility with organic systems. The vinyl functionality allows it to be cured via addition (platinum-catalyzed) or peroxide systems when blended with appropriate crosslinkers.

### KEY FEATURES

- Excellent solvent and fuel resistance
- Enhanced chemical and thermal stability
- Vinyl-reactive functionality for crosslinking
- Low permeability to gases and fluids
- Good compatibility with organic and fluorinated systems
- Wide temperature service range: -60°C to +250°C

### CHEMICAL STRUCTURE



### CAS NUMBER

68951-98-4

### PHYSICAL PROPERTIES

Color and Appearance	Colorless clear liquid
Flash Point	>240°C
Viscosity 25°C, cSt	100-100,000
Density 25°C	1.15
Volatile (200°C, 4h)	<5.0%

## SiSiB® VF6965 Vinyl Fluoro Silicone Fluid

*These values are typical and are not intended for use as specifications.*

### APPLICATIONS

SiSiB® VF6965 is used for defoaming agent, lubricating oil, and grease which can improve the corrosion resistance and solvent resistance. It is also used as an efficient defoaming agent and fabric finishing agent for spin printing and dyeing, which provides smaller surface tension, lower refractive index, and oil resistance and water resistance.

- Base polymer or reactive modifier in fluorosilicone rubbers and gels
- High-performance sealants, potting compounds, and adhesives
- Fuel- and solvent-resistant gaskets and O-rings
- Aerospace and automotive elastomer systems

### PACKING

SiSiB® VF6965 is supplied in 5Kg, 20Kg pails and 200Kg steel drums.

### HANDLING

This document does not contain the product safety information required for safe use. Before handling, please refer to the product and safety data sheets, as well as container labels, for information on safe usage, physical hazards, and health risks. Safety Data Sheet is available on the website, from the distributor, or by contacting SiSiB customer service.

### STORAGE

In the original unopened packaging, SiSiB® VF6965 has a shelf life of 24 months.

### NOTE

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability.

We disclaim liability for any incidental or consequential damages.