

ADDSiL™ 11220

SILICONE SURFACTANT for PU RIGID FOAM

INTRODUCTION

ADDSiL™ 11220 silicone surfactant is a non-hydrolytic polyether polydimethylsiloxane copolymer with high activity.

It is designed for HCFC-141b and cyclopentane blown polyurethane foams; it provides strong nucleation and low thermal conductivity.

FEATURES

Fine Cells Texture	■ ■ ■
Emulsification	■ ■
Solubility	■ ■
Flow Ability	■ ■ ■
Dimensional Stability	■ ■
Void Reduction	■

TYPICAL PHYSICAL PROPERTIES

Appearance	Transparent viscous liquid
Viscosity _{25°C}	1200+/-250 mPa.s
Density _{25°C}	1.04+/-0.03 g/cm ³
Water	< 0.3%
Freezing point	< 0 °C
pH (1% water solution)	6.0+/-2.0

APPLICATIONS

ADDSiL™ 11220 provides excellent nucleation ability. Very fine cells and flow can deliver foams with constantly low thermal conductivities in all areas of the foamed refrigerator cabinet.

ADDSiL™ 11220 provides very good fluidity during the entire foaming process in the reaction system and produce homogeneous density distribution.

The recommended concentration of this product is 2% to 3% of polyol (php).

ADD*SiL*TM 11220

SILICONE SURFACTANT for PU RIGID FOAM

PACKING AND STORAGE

ADD*SiL*TM 11220 surfactant will become hazy when stored at temperatures below 20°C and will solidify to a soft wax at temperatures below 10°C. The product should be warmed to room temperature and stirred before use.

ADD*SiL*TM 11220 is supplied in net weight 200Kg steel drum or 1000Kg IBC tote.

When stored at ambient temperature in the original unopened packing, ADD*SiL*TM 11220 has a shelf life of 12 months from the date of production.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: support@SiSiB.com.