

# ADDSiL™ 8288

## Silicone Leveling Agent

### INTRODUCTION

ADDSiL™ 8288 is a polyether-modified polydimethylsiloxane. It is a silicone additive for ink, paints and coatings to improve leveling and mar resistance.

### BENEFITS

- Increased substrate wetting.
- Avoid cratering.
- Improved surface smoothness and scratch resistance.
- Improved gloss,
- Good compatibility.

### TYPICAL PHYSICAL PROPERTIES

Color and Appearance	Colorless to light yellow clear liquid
Active Ingredient	100%
Viscosity <sub>25°C</sub>	800~2000cst
Refractive Index <sub>25°C</sub>	1.430~1.440
Recommended Levels	0.1~1.0%

### APPLICATION FIELDS

- Solvent-borne coatings.
- Solvent-free coatings.
- Water based coatings.

### APPLICATIONS

ADDSiL™ 8288 is silicone based surface additive for solvent-free and solvent-borne coating systems, printing inks and adhesive system. It can provide strong reduction of surface tension. It provide very good substrate wetting, excellent anti-cartering, and increases surface slip.

### RECOMMENDED LEVELS

**SINOPCC GROUP**

AddSil, CoatSil, Kolark, PowSil, SinoSil, SiSiB, WinSil:  
Trademark of SINOPCC Group Limited or its affiliated.  
© 2018 SINOPCC Group Limited. All rights reserved.  
For further information, please see [www.SiSiB.com](http://www.SiSiB.com).

# ADDSiL™ 8288

## Silicone Leveling Agent

The recommended dosage is 0.1~1.0% of the total formulations.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

It is added during any stage of the production process including post-addition.

### PACKING AND STORAGE

ADDSiL™ 8288 is supplied in 25Kg / 200Kg plastic drum or steel drum or according to customer's request.

In the original unopened packaging, ADDSiL™ 8288 has a shelf life of 24 months.

When stored at temperatures below 10°C ADDSiL™ 8288 will become hazy and solidify to a soft wax. This effect is reversed upon heating and is common to silicone glycol copolymers. Repeated freeze thaw cycles have no effect on product performance.

### NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: [support@SiSiB.com](mailto:support@SiSiB.com).