

ADD*SiL*™ 8311

Silicone Leveling Agent

COMPOSITION

Pure polyether modified polydimethylsiloxane.

BENEFITS

- Reduced surface tension of coating systems.
- Improved substrate wetting.
- Avoids cratering.
- Increased surface slip and gloss.
- Thermostable, can be used for baking system.
- Good recoating and no loss in in adhesion.

TYPICAL PHYSICAL PROPERTIES

Color and Appearance	Slight yellowish paste liquid
Active Ingredient	100%
Density _{25°C}	0.88~0.92g/ml (25% Xylene solution)
Viscosity _{25°C}	5~25s (T-4 viscometer)
Recommended Levels	0.1~0.5% (25% Xylene solution)

EFFECTS (25% XYLENE SOLUTION)

Transparency in clear formulation:	★★★★★
Defoaming effect:	★★
Dynamic surface tension:	★★★
Static surface tension:	★★
Slip effect:	★★★
Reduce orange peel effect:	★★

APPLICATION FIELDS

- Solvent based
- UV Curing

SINOPCC GROUP

AddSil, CoatSil, Kolark, PowSil, SinoSil, SiSiB, WinSil:
Trademark of SINOPCC Group Limited or its affiliated.
© 2018 SINOPCC Group Limited. All rights reserved.
For further information, please see www.SiSiB.com.

ADDSiL™ 8311

Silicone Leveling Agent

APPLICATIONS

ADDSiL™ 8311 is silicone based surface additive for solvent-borne and UV curing system. It can provide strong reduction of the surface tension of coating systems. It therefore particularly improves substrate wetting and avoids cratering. Surface slip and gloss are also increased.

ADDSiL™ 8311 is a thermostable silicone additive which, in contrast to conventional silicones, shows no thermal decomposition at high temperature.

RECOMMENDED LEVELS

The recommended dosage is 0.1~0.5% (25% Xylene solution) of the total formulations.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

The additive can be incorporated during any stage of the production process, including post-addition.

ADDSiL™ 8311 should be diluted before addition (25% Xylene solution is recommended).

PACKING AND STORAGE

ADDSiL™ 8311 is supplied in 20Kg / 180Kg plastic drum or steel drum or according to customer's request.

In the original unopened packaging, ADDSiL™ 8311 has a shelf life of 24 months.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

SINOPCC GROUP

AddSil, CoatSil, Kolark, PowSil, SinoSil, SiSiB, WinSil:
Trademark of SINOPCC Group Limited or its affiliated.
© 2018 SINOPCC Group Limited. All rights reserved.
For further information, please see www.SiSiB.com.

ADD*SiL*™ 8311

Silicone Leveling Agent

Please send all technical questions concerning quality and product safety to:
support@SiSiB.com.