

ADD*SiL*™ 8326

Silicone Leveling Agent

INTRODUCTION

ADD*SiL*™ 8326 is a polyether-modified polydimethylsiloxane solution. It is a highly effective silicone additive, provides a strong reduction of surface tension, therefore it improves the wetting of critical substrates.

BENEFITS

- Strong reduction of surface tension.
- Excellent substrate wetting.
- Prevented cratering.
- Increased surface slip.
- Good defoaming effect.

TYPICAL PHYSICAL PROPERTIES

Color and Appearance	Light yellow clear liquid
Solvent:	Xylene
Active Ingredient	13%
Density _{25°C}	0.86~0.90g/ml
Viscosity _{25°C}	5~25s (T-4 viscometer)
Recommended Levels	0.1~0.5%

EFFECTS

Transparency in clear formulation:	★★★
Defoaming effect:	★★★★★
Dynamic surface tension:	★★★★★
Static surface tension:	★★★★★
Slip effect:	★★★★★
Reduce orange peel effect:	★★

APPLICATION FIELDS

- Solvent-borne coatings.
- UV curing coatings.

SINOPCC GROUP

AddSil, CoatSil, Kolark, PowSil, SinoSil, SiSiB, WinSil:
Trademark of SINOPCC Group Limited or its affiliated.
© 2018 SINOPCC Group Limited. All rights reserved.
For further information, please see www.SiSiB.com.

ADD*SiL*™ 8326

Silicone Leveling Agent

APPLICATIONS

ADD*SiL*™ 8326 can be used in pigmented systems to prevent the formation of Bénard cells and improve leveling.

ADD*SiL*™ 8326 is recommended for polyurethane and epoxy systems.

RECOMMENDED LEVELS

The recommended dosage is 0.1~0.5% of the total formulations.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

It is added during any stage of the production process including post-addition.

PACKING AND STORAGE

ADD*SiL*™ 8326 is supplied in 25Kg / 200Kg plastic drum or steel drum or according to customer's request.

In the original unopened packaging, ADD*SiL*™ 8326 has a shelf life of 24 months.

Separation or turbidity may occur at temperatures below 5°C. Warm to 20°C and mix well.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: support@SiSiB.com.