

POWSIL™-99880

High Concentrate Softener

INTRODUCTION

POWSIL-99880 is an economic, soft and stable textile softener which contains a revolutionary and new generation of silicone molecule that delivers a soft, voluminous and silky hand feel to various fabrics. Furthermore it provides hydrophilicity to most types of textile fabrics. It is very stable in an ordinary textile finish process without causing oil-spots on fabric. Comparable with other finishing agents, it specially can be applied in same bath with wrinkle free finishings

BENEFITS

- Very soft, bulky and silky hydrophilic softener;
- Concentrate but readily to be diluted;
- Very stable in ordinary textile finish process;
- Can be applied in same bath with wrinkle-free resin, binder, etc;
- Deeply penetrate into fibers to impart internal softness;
- Bulky and silky softness as opposed to a greasy feel;
- Excellent affinity to all types of textile;
- Excellent fiber elasticity and shape recovery;
- Durable softness to laundering;
- Less fabric yellowing;
- Good hydrophilicity;
- Outstandingly exhaustible to particularly natural fibers;
- Re-dyeable and over dyeable.

TYPICAL PHYSICAL PROPERTIES

Property	Value
Physical Form	Liquid
Appearance	Clear and light yellowish
Viscosity (25°C,cps)	<500 cst
pH(25°C)	4.0~6.0
Diluents	Water
Ionic	Nonionic to weak cationic

APPLICATION

SINOPCC GROUP

AddSil, CoatSil, Kolark, PowSil, SinoSil, SiSiB, WinSil:
Trademark of SINOPCC Group Limited or its affiliated.
© 2018 SINOPCC Group Limited. All rights reserved.
For further information, please see www.SiSiB.com.

POWSIL™-99880

High Concentrate Softener

Although POWSIL-99880 is a stable and non defective product, it is strongly advised that additional validation both in laboratory and production facilities be conducted carefully to check suitability of POWSIL-99880 for your processes.

POWSIL-59185 can be used as received or pre-diluted with water before applying. The desirable usages are dependent on the required softness of the fabric and yarn after dyeing and rinsing.

1. Pad-dry-cure process

Dosage:	10-30g/l for light fabric or 20-40g/l for heavy fabric
pH:	5.0-7.0
Temp.:	Ambient temperature
Dry/Cure:	120-170°C for 1-3 min

2. Exhaustion process

Dosage:	1.0-4.0% on the weight of fabric
Liquor ratio:	1/10 -1/20
pH:	5.0-7.0
Temp.:	Ambient temperature
Time:	20-30 min
Drying:	100-130°C for 3-5 min

3. Garment washing process

Dosage:	1.0-4.0% on the weight of garment
Duration:	20-30 min
Drying:	100-130°C for 3-5 min

Stripping:

POWSIL-99880 can be stripped off fabric. The stripping formulation is as follows:

NaOH:	5g/l
LABS(30%):	2-5%

Add water and NaOH onto fabric tank and then heat to 100°C for 60 min. Then rinse fabric with acidic water and water.

POWSIL™-99880

High Concentrate Softener

PACKING AND STORAGE

To ensure that the product quality is maintained, the container should be tightly sealed when not in use. It should be stored at normal room temperature, preventing prolonged exposure to extreme heat and cold conditions, which may cause product separation. POWSIL-99880 tends to be sediment on bottom during storage period. If the product is separated, stir the contents to homogeneous. If the product is frozen, thaw it at warm condition and stir after thawed.

POWSIL-99880 is packaged in net weight 50Kg plastic drum.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: support@SiSiB.com.