

SiSiB[®] FS9120

Hydrophobic Fumed Silica

INTRODUCTION

SiSiB[®] FS9120 is a hydrophobic fumed silica after treated with HMDS (Hexamethyldisilazane) based on a hydrophilic fumed silica with a specific surface area of 150m²/g. It's a kind of high purity white colloidal powder.

FEATURES

- Reinforcement in elastomer, can effective prevent from the structuration and prolong the shelf-like of RTV silicone sealants.
- High hydrophobicity and stable thixotropy, using in coating and ink can prevent from anti-caking, anti-sagging, anti-thixotropy.
- High hydrophobicity and rheology in Adhesives and Sealants.
- Improve the homogeneity and stability of pigment.
- Improve the free flow of powder coatings and anti-caking.

TYPICAL PHYSICAL PROPERTIES

CAS No.	68909-20-6
Specific surface area (BET)	105 - 135 m ² /g
pH-Value in 4 % aqueous dispersion	5.5 - 7.5
Loss on drying (2h at 105°C) wt.%	Max. 0.5
Loss on ignition (2h at 1000°C) wt.%	Max. 4.0
Silica content (based on ignited material) wt.%	Min. 99.8
Tamped density (2h at 105°C) g/L	40 - 60
Carbon content (2h at 105°C) wt.%	1.0-2.0

APPLICATIONS

- Elastomer, e.g.: HTV&RTV silicone rubber, SLR.
- Coatings, Printing ink.
- Adhesives and Sealants.
- Negative Toners.
- Powder Coatings.

PACKING AND STORAGE

SINOPCC GROUP

AddSil, CoatSil, Kolark, PowSil, SinoSil, SiSiB, WinSil:
Trademark of SINOPCC Group Limited or its affiliated.
© 2018 SINOPCC Group Limited. All rights reserved.
For further information, please see www.SiSiB.com.

SiSiB® FS9120

Hydrophobic Fumed Silica

SiSiB® FS9120 is supplied in multiple layer 10 kg bags.

20'ft GP container can load 1800kg with 10 pallets; 40'ft HQ container can load 4000kg with 20 pallets.

In the original unopened packaging, SiSiB® FS9120 has a shelf life of 24 months under dry conditions.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: support@SiSiB.com.