

SiSiB[®] LR2335

*LSR for Cable Accessories
- Medium & Low Voltage Semi-conductive*

KEY FEATURES

- Volume resistance < 100Ω.CM.
- High tensile strength.
- High flexibility and rebound.
- Good thermal stability and aging resistance.
- Stable electric resistance.

TYPICAL PHYSICAL PROPERTIES

Product	LR2335
Color	Black
Hardness (Shore A)	36 ~ 42
Tensile Strength (MPa)	Min. 6.5
Elongation (%)	Min. 640
Tear Strength (kN/m)	Min. 28
Compression Set at 120°C 300% tensile after 24 Hours (%)	Max. 12
Volume Resistivity (Ω.cm)	Max. 100

Curing condition: 10 minutes at 140°C and post cure 4 hours at 200°C.

APPLICATIONS

- Semi conductive stress cone, shielding of intermediate joint for 35 kV and below.

PACKING AND STORAGE

SiSiB[®] LR2335 is supplied in 20Kg box, with plastic bag inside.

In the unopened original container it has a shelf life of one year in a dry and cool place.

NOTES

All information in the leaflet is based on our present knowledge and experience. We

SiSiB[®] LR2335

LSR for Cable Accessories - Medium & Low Voltage Semi-conductive

reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: support@SiSiB.com.