

SiSiB[®] LR32xx

LSR for Medical Tube

KEY FEATURES

- Excellent transparency.
- Good tensile, anti-tear and rebound.
- ISO10993.
- GB/T16886.10 - 2000 and GB/T16886.5 - 2003.
- USP CLASS VI.

TYPICAL PHYSICAL PROPERTIES

Product	LR3260	LR3270	LR3278
Hardness (Shore A)	60 ~ 64	68 ~ 70	76 ~ 80
Tensile Strength (MPa)	Min. 9	Min. 10	Min. 10
Elongation (%)	Min. 700	Min. 700	Min. 600
Tear Strength (kN/m)	Min. 40	Min. 40	Min. 40
Tensile Set (%)	Max. 5	Max. 5	Max. 7
Rebound (%)	Min. 40	Min. 48	Min. 50

Curing condition: 10 minutes at 140°C and post cure 4 hours at 200°C.

APPLICATIONS

- For laryngeal mask tube or various tracheal intubation.

PACKING AND STORAGE

SiSiB[®] LR3260 is supplied in 20Kg box, with plastic bag inside.

In the unopened original container it has a shelf life of one year in a dry and cool place.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular

SINOPCC GROUP

AddSil, CoatSil, Kolark, PowSil, SinoSil, SiSiB, WinSil:
Trademark of SINOPCC Group Limited or its affiliated.
© 2018 SINOPCC Group Limited. All rights reserved.
For further information, please see www.SiSiB.com.

SiSiB[®] LR32xx

LSR for Medical Tube

purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: support@SiSiB.com.