

SiSiB[®] LR73xx

LSR for Conductive PCR & DR Roller

DESCRIPTION

It is a two parts and platinum curable liquid silicone rubber for injection molding process.

KEY FEATURES

- High rebound
- Low volatility
- High temperature resistance

TYPICAL PHYSICAL PROPERTIES

Product	LR7345	LR7350	LR7365
Appearance	Black	Black	Black
Hardness (Shore A)	44-45	49-51	62-64
Viscosity (Pa.s) A	40-44	66-70	250-270
Viscosity (Pa.s) B	41-44	66-70	250-270
Tensile Strength (MPa)	Min. 4.5	Min. 4.5	Min. 5.0
Elongation at Break (%)	Min. 140	Min. 150	Min. 150
Tear Strength (KN/m)	Min. 6.0	Min. 5.5	Min. 8.0
Linear Shrinkage (%)	Max. 2.5	Max. 2.5	Max. 2.5
Rebound (%)	Min. 60	Min. 68	
Volume Resistivity (Ω cm)	0.00-0.01	0.00-0.01	0.03-0.07

Curing condition: 10 minutes at 140°C and post cure 4 hours at 200°C.

APPLICATIONS

PCR and DR roller

PACKING AND STORAGE

These products are supplied in 20Kg box, with plastic bag inside.

In the unopened original container it has a shelf life of one year in a dry and cool place.

SiSiB[®] LR73xx

LSR for Conductive PCR & DR Roller

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: support@SiSiB.com.