


# SiSiB<sup>®</sup> PC19592

Silicone Emulsifier

INCI: PEG-10 Dimethicone

## CHEMICAL STRUCTURE



## INTRODUCTION

SiSiB<sup>®</sup> PC19592 is a lipophilic polyether-polydimethylsiloxane which has excellent W/Si and W/O emulsibility. The product has slight characteristic odor.

## ADVANTAGES

- Polyether polydimethylsiloxane
- Excellent W/Si, W/O emulsibility
- Easy to emulsify and low operating temperature
- Silky and non-sticky skin feel

## TYPICAL PHYSICAL PROPERTIES

Appearance	Transparent to translucent liquid
Color	Colorless to yellowish
Refractive index	1.4100-1.4300
Specific gravity (25°C)	1.00-1.05
Viscosity (cSt, 25°C)	400~1600
Flash point(°C, Opened cup)	>200

**SINOPCC GROUP**

AddSil, CoatSil, Kolark, PowSil, SinoSil, SiSiB, WinSil:  
Trademark of SINOPCC Group Limited or its affiliated.  
© 2018 SINOPCC Group Limited. All rights reserved.  
For further information, please see [www.SiSiB.com](http://www.SiSiB.com).

# SiSiB<sup>®</sup> PC19592

## Silicone Emulsifier

INCI: PEG-10 Dimethicone

### APPLICATIONS

SiSiB<sup>®</sup> PC19592 can be used in a wide range of personal care applications such as skin care, color cosmetics and sun care and so on.

#### □ How to use:

Slowly add the water phase into the oil phase, and then stir the mixture quickly till uniform. Speeding up the stirring can improve the stability of the emulsion system.

Stir the oil and emulsifier thoroughly before adding water to emulsify.

If all the ingredients are liquid, emulsification can be operated at room temperature without homogenizer. Quick stirring can attain stable emulsion.

Electrolytes, preferably NaCl at a level of 0.5%-2% should be added to the water phase to attain storage stability. Adding some antifreeze agents such as propanediol and glycerin can improve the antifreeze effect of the finished product. Increasing the water proportion can improve viscosity of the system.

#### □ Recommend Dosage:

The recommended usage level of this product is 1%-4% when it's used as major emulsifier, and 0.1%-1.5% as auxiliary emulsifier (according to the total amount of the formulation).

### PACKING AND STORAGE

SiSiB<sup>®</sup> PC19592 is supplied in 20Kg plastic pail or 200Kg steel drum.

In the original unopened packaging, SiSiB<sup>®</sup> PC19592 has a shelf life of 12 months in a dry and cool place at room temperature.

### NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

# SiSiB<sup>®</sup> PC19592

## *Silicone Emulsifier*

*INCI: PEG-10 Dimethicone*

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: [support@SiSiB.com](mailto:support@SiSiB.com).