


# SiSiB<sup>®</sup> PC5010

## *gamma-Chloropropyltrichlorosilane*

### CHEMICAL STRUCTURE



### INTRODUCTION

SiSiB<sup>®</sup> PC5010 is a clear colorless liquid.

### TYPICAL PHYSICAL PROPERTIES

CAS No.	2550-06-3
EINECS No.	219-844-8
Formula	C <sub>3</sub> H <sub>6</sub> Cl <sub>4</sub> Si
Molecular Weight	211.98
Boiling Point	182°C [760mmHg]
Flash Point	84°C
Color and Appearance	Colorless transparent liquid
Density <sub>25/25°C</sub>	1.359
Refractive Index	1.4668 [25°C]
Min. Purity	99.0%

### APPLICATIONS

SiSiB<sup>®</sup> PC5010 can be used as an intermediate for other functional organosilanes, such as SiSiB<sup>®</sup> PC5011, SiSiB<sup>®</sup> PC5012 etc.

### PACKING AND STORAGE

SiSiB<sup>®</sup> PC5010 is supplied in 260Kg steel drum.

In the unopened original container SiSiB<sup>®</sup> PC5010 has a shelf life of one year in a dry and cool place.

**SINOPCC GROUP**

AddSil, CoatSil, Kolark, PowSil, SinoSil, SiSiB, WinSil:  
Trademark of SINOPCC Group Limited or its affiliated.  
© 2018 SINOPCC Group Limited. All rights reserved.  
For further information, please see [www.SiSiB.com](http://www.SiSiB.com).

# SiSiB<sup>®</sup> PC5010

*gamma-Chloropropyltrichlorosilane*

## NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: [silanes@SiSiB.com](mailto:silanes@SiSiB.com).