


# SiSiB<sup>®</sup> PC6100

## Vinyltrichlorosilane

### CHEMICAL STRUCTURE



### INTRODUCTION

SiSiB<sup>®</sup> PC6100 is a colorless clear liquid.

### TYPICAL PHYSICAL PROPERTIES

CAS No.	75-94-5
EINECS No.	200-917-8
Formula	C <sub>2</sub> H <sub>3</sub> Cl <sub>3</sub> Si
Molecular Weight	161.49
Boiling Point	93°C [760mmHg]
Flash Point	21°C
Color and Appearance	Colorless transparent liquid
Density <sub>25/25°C</sub>	1.2426
Refractive Index	1.4295 [25°C]
Min. Purity	99.0%

### APPLICATIONS

SiSiB<sup>®</sup> PC6100 can be used as raw material for SiSiB<sup>®</sup> PC6110 (Vinyltrimethoxysilane), SiSiB<sup>®</sup> PC6120 (Vinyltriethoxysilane) etc.

### PACKING AND STORAGE

SiSiB<sup>®</sup> PC6100 is supplied in net weight 240Kg steel drum.

In the unopened original container SiSiB<sup>®</sup> PC6100 has a shelf life of one year in a dry and cool place.

# SiSiB<sup>®</sup> PC6100

## *Vinyltrichlorosilane*

### NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: [silanes@SiSiB.com](mailto:silanes@SiSiB.com).