


# SiSiB<sup>®</sup> PC8151

## Phenyltriisopropenoxysilane

### CHEMICAL STRUCTURE



### INTRODUCTION

SiSiB<sup>®</sup> PC8151 is colorless or yellowish clear liquid.

### TYPICAL PHYSICAL PROPERTIES

CAS No.	52301-18-5
EINECS No.	411-340-8
Formula	C <sub>15</sub> H <sub>20</sub> O <sub>3</sub> Si
Molecular Weight	276.40
Boiling Point	298.5°C [760mmHg]
Flash Point	135.2°C
Color and Appearance	Colorless or yellowish clear liquid
Density <sub>25/25°C</sub>	0.996g/cm <sup>3</sup>
Refractive Index	1.496[25°C]
Min. Purity	95.0%

### APPLICATIONS

SiSiB<sup>®</sup> PC8151 can be used as crosslinkers in RTV-1 silicone rubber.

### PACKING AND STORAGE

SiSiB<sup>®</sup> PC8151 is supplied in net weight 150Kg steel drum.

In the unopened original container SiSiB<sup>®</sup> PC8151 has a shelf life of one year in a dry and cool place.

# SiSiB<sup>®</sup> PC8151

## *Phenyltriisopropenoxysilane*

### NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: [silanes@SiSiB.com](mailto:silanes@SiSiB.com).