

# SiSiB<sup>®</sup> SF0206

## Long-chain Alkyl Silicone Fluid

### INTRODUCTION

SiSiB<sup>®</sup> SF0206 is a long chain alkyl (C12) functional silicone fluid of medium viscosity whose special chemical structure imbues it with the benefits of silicone fluids and mineral oils.

SiSiB<sup>®</sup> SF0206 is used for thermal molding of rubber, plastics and low-melting nonferrous metals. It is superior to conventional silicone fluids when the finished parts are subsequently to be painted, printed, coated or bonded. An outstanding release effect is even obtained when extremely small amounts of the release agent are used. The result is an easy, accurate reproduction of every surface detail of the molded article. SiSiB<sup>®</sup> SF0206 exhibits excellent film forming properties.

### TYPICAL PHYSICAL PROPERTIES

Appearance	Clear liquid
Color	Light yellow
Active ingredient (%)	100
Viscosity (25°C, cSt)	900~1500
Specific gravity(25°C/77°F)	0.890~0.950
Refractive Index $n_D^{25}$	1.453~1.455
Volatile (150°C, 3h)	Max.1.0%

### APPLICATIONS

SiSiB<sup>®</sup> SF0206 can be used as release agent in the production of floor mats and tiles, seals, grommets, gaskets, toys, paneling, decorative trim, household appliance assemblies and similar plastic and rubber products that are coated, painted, plated or bonded.

SiSiB<sup>®</sup> SF0206 can be used as parting agent in die casting of aluminum, zinc, magnesium and other metals.

SiSiB<sup>®</sup> SF0206 can be formulated into automotive polish products for use in garages and body shops where polydimethylsiloxanes could give rise to re-coatability problems.

When added as a built-in lubricant the fluid can facilitate the assembly of mechanical components and can act as a lubricant in service.

AddSil, CoatSil, Kolark, PowSil, SinoSil, SiSiB, WinSil:  
Trademark of SINOPCC Group Limited or its affiliated.  
© 2018 SINOPCC Group Limited. All rights reserved.  
For further information, please see [www.SiSiB.com](http://www.SiSiB.com).

# SiSiB<sup>®</sup> SF0206

## *Long-chain Alkyl Silicone Fluid*

### PACKING AND STORAGE

SiSiB<sup>®</sup> SF0206 is supplied in 20Kg plastic pail or 180Kg steel drum.

When stored at ambient temperature in the original unopened packing, SiSiB<sup>®</sup> SF0206 has a shelf life of 12 months from the date of production.

### NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: [support@SiSiB.com](mailto:support@SiSiB.com).