

SiSiB[®] SR8622

Silicone MQ Resin

INTRODUCTION

SiSiB[®] SR8622 is a co-hydrolysis product of tetraalkoxy silane (Q unit) and trimethyl alkoxy silane (M unit). It is the kinetic reaction products of silicates with trimethyl siloxy groups which generate a silicon-based, cross-linked three dimensional network.

SiSiB[®] SR8622 can be compounded with polydimethylsiloxanes or dissolved in appropriate solvents like aromatic and no-aromatic hydrocarbons or lower alcohols.

FEATURES

- Excellent reinforcing effectiveness for silicone rubber.
- Compatible with silicone and organic carriers.
- Cures to give a durable film
- Thermal stability up to 300°C
- Good weatherability
- Good electrical property
- Water repellency

TYPICAL PHYSICAL PROPERTIES

Appearance	White powder
Viscosity, 60% in xylene @ 25°C	8~19 cSt
M:Q ratio	(0.8-1.0):1.0
Molecular Weight	5000~8000
OH content	1~2%
Volatile @ 150°C, 2h	<1.0%

APPLICATIONS

SiSiB[®] SR8622 can be used as reinforcing filler of silicone pressure sensitive adhesives.

SiSiB[®] SR8622 can be used as intermediate of protective coatings for scratch resistance, insulation resistance, etc.

SiSiB[®] SR8622 can be used as additives of releasing agents, deformers, releasing modifiers, etc.

SiSiB[®] SR8622

Silicone MQ Resin

SiSiB[®] SR8622 can be used as treatment of granular materials for water repellency.

PACKING AND STORAGE

SiSiB[®] SR8622 is supplied in 25Kg fiber drum.

In the unopened original container SiSiB[®]SR8622 has a shelf life of 18 months in a dry and cool place.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: support@SiSiB.com.